

| třída dle<br>EN 206-1 | třída dle<br>ČSN 73 1201 | značka dle<br>ČSN 73 62 06 (Z2) |
|-----------------------|--------------------------|---------------------------------|
| -                     | ( B 3 )                  | 60                              |
| -                     | B 5                      | 80                              |
| -                     | B 7,5                    | 105                             |
| -                     | B 10                     | 135                             |
| -                     | B 12,5                   | (160)                           |
| ( C 13,5 )            | ( B 13,5 )               | 170                             |
| C 12/15               | B 15                     | (200)                           |
| C 16/20               | B 20                     | 250                             |
| C 20/25               | B 25                     | (300)                           |
| ( C - /28 )           | ( B 28 )                 | 330                             |
| C 25/30               | B 30                     | (350)                           |
| ( C - /35 )           | B 35                     | 400                             |
| C 30/37               | ( B 37 )                 | (425)                           |
| ( C - /40 )           | B 40                     | (450)                           |
| C 35/45               | B 45                     | 500                             |
| C 40/50               | B 50                     | (550)                           |
| C 45/55               | B 55                     | 600                             |
| C 50/60               | B 60                     | (650)                           |

Převodní tabulka betonů dle jejich tříd

| CSN, norma      | Značka betonu |       |         |          |         |         |          |           |         |         |         |         |         |
|-----------------|---------------|-------|---------|----------|---------|---------|----------|-----------|---------|---------|---------|---------|---------|
|                 | c             | d     | e       | f        | g       | h       | i        | j         | k       | l       | m       | n       | o       |
| ČSN 1090        |               |       |         |          |         |         |          |           |         |         |         |         |         |
| ČSN 73 24 00    | 60            | 105   | 135     | 170      | 250     | 330     |          | 500       |         | 600     |         |         |         |
| ČSN 73 12 01-87 | Třída betonu  |       |         |          |         |         |          |           |         |         |         |         |         |
|                 | 01            | 0     | I       | II       | III     | IV      | V        | VI        | VII     | VIII    | IX      | X       | XI      |
| ČSN 73 12 01-88 |               | B 7,5 | B 10    | B 15     | B 20    | B 25    | B 30     | B 35      | B 40    | B 45    | B 50    | B 55    | B 60    |
| EC-NAD skutečné |               |       |         | C -/13,5 | C 16/20 |         | C -/28   |           | C 35/45 |         | C 45/55 |         |         |
| EC-NAD normové  |               |       | C 8/10  | C 12/15  | C 16/20 | C 20/25 | C 25/30  | C 30/37   | C 30/37 | C 35/45 | C 40/50 | C 45/55 | C 50/60 |
| Pokračování     |               |       |         |          |         |         |          |           |         |         |         |         |         |
| EC-NAD normové  |               |       | C 55/67 | C 60/75  | C 70/85 | C 80/95 | C 90/105 | C 100/115 |         |         |         |         |         |